

LOOP

Technical sheet

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	64.7% Acrylic, 33.6% Polyester, 1.7% Lycra			
Weave	Loop knit			ISO 7211-1
Weight	732		g/m ²	ISO 3801
Width	160		cm	EN 1773
Roll length	27		ml	

FABRIC RESISTANCE

seam slippage weft knit and warp knit	75	75	LBF	ASTM 4034
Tear strength weft knit and warp knit	25	20	LBF	ASTM D2261
Break strength weft knit and warp knit	200	115	LBF	ASTM D5034
Spray test	3		Class / 5	ISO 4920

COLOUR-FASTNESS

Colour fastness under dry friction	5		Class / 5	ISO 105X12
Colour fastness under wet friction	5		Class / 5	ISO 105X12

USES

Guarantee	5	years	
Recommended Uses	Seating, cushions		

CARE



WARRANTY

5

YEARS



COLOUR-FASTNESS

Colorfastness to Light	Grade 4 @ 2200 kJ		AATCC 169-2003 Option 3
Colorfastness to Light (SAE)	Grade 4/5 @ 1500 kJ		SAE 1960J

This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK