

LOOP

Karta techniczna

CHARAKTERYSTYKA	WARTOŚCI		JEDNOSTKI	STANDARDY
	OSNOWA	WĄTEK		

OGÓLNA CHARAKTERYSTYKA

Skład	64,7% akryl, 33,6% poliester & 1.7% Lycra		
Splot	Dzianina petelkowa		ISO 7211-1
Gramatura	732	g/m ²	ISO 3801
Szerokosc rolki	160	cm	EN 1773
Długosc rolki	27	ml	

ODPORNOSC TKANINY

Splecenie serii/wielu petli	75	75	LBF	ASTM 4034
Rozerwanie serii/wielu petli	25	20	LBF	ASTM D2261
Wytrzymałosc na zerwanie serii/wielu petli	200	115	LBF	ASTM D5034
Test natrysku	3		Class / 5	ISO 4920

ODPORNOSC KOLORÓW

Odpornosc kolorów na tarcie na sucho	5		Class / 5	ISO 105X12
Odpornosc kolorów na tarcie na mokro	5		Class / 5	ISO 105X12

UZYTKOWANIE

Gwarancja	5	Lat	
Zalecane uzytkowanie	Poduszki, Siedzenia		

CARE



WARRANTY

5

YEARS



ODPORNOSC KOLORÓW

Odpornosc na blakniecie	Grade 4 @ 2200 kJ	Grade 4/5 @ 1500 kJ		AATCC 169-2003 Option 3
-------------------------	-------------------	---------------------	--	-------------------------

This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK