

ORIGIN

Technical sheet

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	50% solution dyed acrylic Sunacryl / 50% recycled solution dyed acrylic Sunacryl			
Backing / Finish	Non PFAS - Cleangard special dirt-resistant and water repellent treatment			
Weave	Canvas			ISO 7211-1
Weight	280		g/m ²	ISO 3801
Thickness	0.60		mm	ISO 5084
Width	120		cm	EN 1773
Roll length	60		ml	

FABRIC RESISTANCE

Tensile strength	140	90	daN/5cm	ISO 13934-1
Elongation at break	23	20	%	ISO 13934-1
Tear strength	4.00	2.50	daN	ISO 13937-1
Stiffness	1250	800	mN	ISO 2493
Elongation under load	3	7	%	MO LAB 025
Schmerber	>330		mm	ISO 811
Spray test	4-5		Class / 5	ISO 4920
Resistance durability	4		Class / 4	EN 13561

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4-5		Class / 5	ISO 105 B04
Colour fastness UV - indoor	7-8		Class / 8	ISO 105 B02
Colour fastness under dry friction	5		Class / 5	ISO 105X12
Colour fastness under wet friction	5		Class / 5	ISO 105X12
Colour durability	4		Class / 4	EN 13561

USES

Guarantee	10	years	
Recommended Uses	Drop arm awning, Folding arm awning, Dutch canopy, Fixed awning, Exterior velum, Pergola, Conservatory blind, Sail shade, Umbrella, Roller blind.		

This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK



STANDARD 100
CQ 638/10
IFTH

