

SAVANE

Technical sheet



CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	100% Sunbrella Acrylic		
Backing / Finish	Non PFAS - Water-repellent & Stain-proof		
Weave	Jacquard		ISO 7211-1
Weight	430	g/m ²	ISO 3801
Width	140	cm	EN 1773
Roll length	40	ml	

FABRIC RESISTANCE

Tensile strength	100	236	daN/5cm	ISO 13934-1
Elongation at break	18	29	%	ISO 13934-1
Pilling	5		Class / 5	ISO 12945-2
Spray test	5		Class / 5	ISO 4920
Seam slippage (180 N)	< 5	< 3	mm	ISO 13936-2
Stitching strength	475	375	N	ISO 13935-2
Stability on 30 deg. C washing	-2	-0.80	%	ISO 5077

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4/5		Class / 5	ISO 105 B04
Colour fastness UV - indoor	8		Class / 8	ISO 105 B02
Colour fastness under dry friction	5		Class / 5	ISO 105X12
Colour fastness under wet friction	5		Class / 5	ISO 105X12
Colour fastness 30°C washing	5		Class / 5	ISO 105 C06

FIRE RESISTANCE

California Technical Bulletin 117-203 Section 1	Pass
NFPA 260 Classe I	Pass
NF EN 1021-1	Pass
BS 5852 Part 1 Source 0	Pass

USES

Guarantee	5	years
Recommended Uses	Seating, Cushions, Curtains	

CARE



This product's values may vary with a tolerance of $\pm 5\%$

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK



STANDARD 100
CQ 638/8
IFTH

