

SUNWORKER

Technical sheet



CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	high-tenacity polyester/PVC 50/50			
Backing / Finish	Double-sided PVC coating - Lowick system			
Weave	Rachel Trameur - superior tear resistance			ISO 7211-1
Weight	300		g/m ²	ISO 3801
Width	150 300		cm	EN 1773
Roll length	60 30		ml	

FABRIC RESISTANCE

Tensile strength	220	150	daN/5cm	ISO 13934-1
Elongation at break	32	30	%	ISO 13934-1
Tear strength	43.00	22.00	daN	ISO 13937-1
Stiffness	1100	450	mN	ISO 2493
Acoustic absorption	0.15			ISO 354

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4-5		Class / 5	ISO 105 B04
--------------------------------------	-----	--	-----------	-------------

USES

Guarantee	5	years	
Recommended Uses	Bimini, external windshield and window cover		

This product's values may vary with a tolerance of $\pm$ 5%

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

