

SUR LAST

Technical sheet

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		



GENERAL CHARACTERISTICS

Composition	100% polyester teint masse		
Backing / Finish	Polyuréthane coating		
Weight	240.00	g/m ²	ISO 3801
Width	152	cm	EN 1773
Roll length	90	m	

FABRIC RESISTANCE

Tensile strength	217.00	152.00	daN/5cm	ISO 13934-1
Tear strength	9.90	8.70	daN	ISO 13937-1
Schmerber	850		mm	ISO 811

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4	Class / 5	ISO 105 B04
--------------------------------------	---	-----------	-------------

USES

Guarantee	3	years	
Recommended Uses	Bimini top, Console cover, Seat cover		

This product's values may vary with a tolerance of \pm 5%

Dickson-Constant SAS, [French limited-liability corporation] with capital of €12,640,000 - Metropolitan community of Lille business registration

10, rue des Châteaux - BP 109 - Z.I la Pilaterie 59443 Wasquehal cedex - France

Tél. : +33.(0)3.20.45.59.59 - Fax : +33.(0)3.20.45.59.00 - www.dickson-constant.com/en/UK

